UNIPLAN 350 DR

Pumpable rapid drying, fibre-reinforced, dust-reduced, cement-based, self-levelling compound for thicknesses from 6 to 60 mm per layer





BENEFITS AND FEATURES

- Application thickness from 6 to 60 mm per layer
- Dust-reduced
- Suitable for hand- or pump application
- Excellent self-levelling properties
- Excellent surface finish
- Ready for covering after 1 - 5 days, up to 30 mm 1 day, up to 40 mm 2 days, up to 50 mm 3 days, up to 60 mm 5 days
- Fibre-reinforced
- Suitable for floating floors (minimum layer thickness 30 mm)
- Suitable for heated floors
- Suitable for flat levelling and slope building
- High bonding strength to the substrate
- High compressive and flexural strength
- Suitable for all kinds of floorings, resilient, textiles, floating parquet and laminate, ceramic and natural stone, and glued multi-layer parquet
- Very low emissions - EMICODE EC1 Plus
- Product-specific EPD
- Residual Greenhouse Gas emissions fully offset

CO_2e FULLY OFFSET PRODUCTS

Residual Greenhouse Gas emissions measured throughout the life cycle of this product using Life Cycle Assessment (LCA) methodology, verified and certified with EPDs, have been offset for the year 2026 through the acquisition of carbon credits in support of forestry protection projects. For more details on emission calculations and offsetting projects, visit mapei.com.

CLASSIFICATION ACCORDING TO EN 13813

Uniplan 350 DR is a self-levelling compound, as described in this technical data sheet; it is classified as CT-C30-F7-$A1_{FL}$ according to European norm EN 13813 *"Screed material and floor screeds - Screed material - Properties and requirements"*.

WHERE TO USE

Uniplan 350 DR is intended for interior use for levelling and smoothing differences in thicknesses from 6 to 60 mm on new or existing substrates in residential housing, offices, commercial and public buildings indoors, and can be used for both mechanical adhesion to the substrate and floating constructions (with a layer thickness of at least 30 mm).
Uniplan 350 DR is suitable for heated floors and can be used for embedding electrical or waterborne underfloor heating in dry and wet rooms.
Uniplan 350 DR is suitable to receive all kinds of resilient floor covering types, floating parquet and laminate, ceramic and natural stone as well as glued multi-layer parquet.

Some application examples

- Levelling cementitious levelling compounds or screeds.
- Levelling concrete slabs, lightweight concrete, leca slabs, old terrazzo, ceramic and natural stone slabs.
- Levelling gypsum-based substrates.
- Levelling and embedding underfloor heating systems.
- Levelling floating constructions and acoustic underlays.
- Levelling old and new wooden substrates; timber floors, cross-laminated timber, floorboards, parquet, chipboards for floors, plywood boards.
- Levelling old and new PVC coverings and flooring plasterboards.

TECHNICAL CHARACTERISTICS

Uniplan 350 DR is a grey powder made up of special binders with rapid setting and hydration, with selected graded sand, polymers and special additives prepared according to a formula developed in MAPEI's own R&D laboratories.
When mixed with water, **Uniplan 350 DR** becomes a fluid and easily workable self-levelling compound and with high bonding strength to the substrate.

RECOMMENDATIONS

- Do not add more water to a mix which has already begun to set.
- Do not add lime, cement, gypsum, or other binders to the mix.
- Do not use **Uniplan 350 DR** on exterior levelling works.
- Do not use **Uniplan 350 DR** on substrates subject to continuous capillary rising damp (contact MAPEI Technical Services Department).
- Do not use **Uniplan 350 DR** on dusty or crumbling surfaces, or on surfaces with oil or grease stains.
- Do not use **Uniplan 350 DR** when the temperature is below +10°C.
- Do not use **Uniplan 350 DR** on textiles or on other deformable substrates such as asphalt (contact MAPEI Services Department).
- For adhesion to metal substrates contact MAPEI Services Department.
- Do not use **Uniplan 350 DR** as a final wearing top layer.
- **Uniplan 350 DR** must be covered with a suitable floor covering as soon as conditions permit. For drying-out requirements of substrates and **Uniplan 350 DR** before installation of floor covering, refer to current requirements according to local standard.
- The finished, hardened surface must be prepared according to the covering manufacturer's recommendations.

- Do not apply an additional layer of **Uniplan 350 DR** when the previous one is completely dry; in this case, before applying any further levelling layers, first prime the surface with a suitable primer such as **Primer E-10** (diluted 1:1 with water), **Primer G** (diluted 1:1 with water) or **Eco Prim T Plus** (diluted up to 1:4 with water). Wait at least 24 hours (at +23°C and 50 % RH) and make sure the surface is dry enough to absorb the primer.
- Do not expose the surface to draughts or direct sunlight before, during and 1 to 3 days after application.
- Do not use dehumidifiers before, during and 3 days after application.
- Do not use gas heating before, during and after application.
- Do not turn on electrical underfloor heating three days before to one to two weeks after application of the levelling compound (when tiling, electrical underfloor heating may normally be turned on only 28 days after tile grouting). Waterborne underfloor heating may be turned on at ambient temperature when applying the levelling compound. Approx. one week after laying, the heat can be gradually increased to operating temperature.
- The specified minimum layer thickness of 6 mm applies to local high points. When applying large areas with a mixer pump or pump truck, and where the substrate is relatively flat, a layer thickness of at least 10 mm is recommended to achieve a satisfactory result.
- Always install a waterproofing membrane on top of the compound in wet rooms.
- Temperature and relative humidity should always be measured and recorded in the laying protocol before application.
- The material in powder form should be stored in heated areas prior to application. Strongly cooled material carries the risk that certain additives will not be able to dissolve properly during mixing. Too high temperature in the material changes the flow properties, e.g. that the material gets a shorter processing time and sets too early.
- If **Uniplan 350 DR** is used as a floating floor, it can be applied in thicknesses from 30 to 60 mm on a separating layer. In addition, consider necessary actions depending on drying conditions, the day after application, to reduce the risk of edging and cracking (contact MAPEI Technical Services Department).

APPLICATION PROCEDURE

Preparing the substrate

Substrates must comply with the specifications contained in the applicable local standards.
Substrates must be sound and have sufficient load-bearing capacity, be dry, clean, and free of all traces of dust, laitance, loose or detached parts, paints and varnishes, wax, grease, oil, rust, gypsum residues and all other pollutants that can reduce adhesion. Remains of old coverings and coatings, and other pollutants should be removed mechanically, if necessary, for example by shot blasting, milling, or grinding. Cementitious-based surfaces that are not sufficiently sound must be removed or, where possible, consolidated with a suitable MAPEI-system (such as **Eco Prim PU 1K**, **Primer MF EC Plus** or **Primer 3296**). Finish off by thoroughly vacuuming the substrate.
Surface tensile strength of the substrate must be at least 0.5 N/mm² (MPa).
Repair any cracks present in the substrate with **Mapepoxy BI-IMP** or a suitable injection product, and where required reinforce with **Rete 320**.
Use height marks to determine the level that is required to achieve the prescribed floor tolerances for the finished floor according to local standard.
Use dividers to divide the area of application into sections if needed.
On floating floors install a compressible band carefully seal around the perimeter of the rooms to be laid and around any vertical elements which pass through the floor (such as pillars, columns and drainages).

Priming the substrate

Prime concrete and cementitious-based substrates with a suitable primer such as **Primer E-10** (diluted 1:1 with water), **Eco Prim T Plus** (diluted up to 1:4 with water), or **Primer G** (diluted 1:1 with water), see technical data sheet for more information, to hold the dust, to achieve sufficient adhesion and to equalize absorption in the substrate. The primer can be applied with a brush, roller, or spraying device. The primer should be brushed or rolled thoroughly into the substrate. When spraying, smooth out the primer with a brush. Please note to avoid puddles from forming. Ensure the primer is dry before applying the levelling compound, always refer to the drying time reported in the technical data sheet. Pores and pinholes are usually the result of insufficient, thin or over-diluted priming, low substrate temperature or a combination of all these. The primer should have dried sufficiently before application of **Uniplan 350 DR**. If it takes more than 3 - 4 hours for the primer to dry, indicates that the drying conditions are not good enough for it to dry out correctly or that the substrate is not able to absorb the primer properly.

Gypsum-based screeds may only be levelled off with **Uniplan 350 DR** after sanding the surface and applying a suitable primer such as **Eco Prim T Plus** (diluted up to 1:2 with water) or **Primer G** (undiluted).
Prime existing ceramic and natural stone substrates with a coat of a suitable primer such as **Eco Prim T Plus** or **Eco Prim Grip Plus** after cleaning the surface with a suitable detergent and, if required, abrading the surface mechanically. Alternatively prime with a suitable resin-based primer, such as **Mapeprimer M** or **Primer SN**, followed by a full broadcast of dry quartz sand **Sand 0.8 - 1.2 mm**. Remove excess quartz sand with vacuuming.
Prime existing resilient PVC coverings with a coat of a suitable primer such as **Eco Prim T Plus** or **Eco Prim Grip Plus** after cleaning the surface with a suitable detergent and, if required, abrading the surface mechanically.
Wooden substrates must be clean and solidly fixed; any paints, oil or waxes must be removed, and open joints must be sealed with a suitable MAPEI patching compound prior to the application of **Uniplan 350 DR**.

Preparing the mix

Pour the content of a 20 kg bag of **Uniplan 350 DR** into a container with 3.8 - 4.0 liters of clean water (19 - 20 %) and continue mixing with a low-speed electric mixer for min. 2 - 3 minutes until a homogenous, flowable, lump-free mix is formed. Let it stand for 2 - 3 minutes and before applying, remix the blend for a few minutes more.
Uniplan 350 DR can also be mixed using a suitable automatic mixer pump with min. 40 m hose length, or pump truck with min. 60 m hose length. Set the water content to 19 - 20 %. During mixing, check the water content by testing the flow ratio. If the water content is correct, the flow ratio should be 125 - 140 mm (acc. to EN 12706, flow ring 30 x 50 mm) or 140 - 155 mm (acc. to SS 923519, flow ring 50 x 22 mm). While testing the flow ratio, also check that the mix is free of separation and completely homogenous before applying. Smoothen the mix within approx. 20 minutes (at approx. +23°C and 50 % RH). By application of slopes, the water content can be reduced to 3.2 - 3.6 liters of clean water per 20 kg bag (16 - 18 %).
The pot life of the mix varies according to the temperature and reduces as the temperature increases. Do not add more water than the amount required to achieve a good result. Too much water will cause separation and reduce the strength properties of the compound which again could lead to a weaker surface as well as higher shrinkage which increases the risk for cracks.

Applying the mix

Spread **Uniplan 350 DR** by hand or with a pump in a single layer of 6 to 60 mm, and whilst working smooth the surface with a wide toothed spatula or trowel to obtain a smooth finish, and to remove any foam in the surface layer and streaks from the hose.
Make sure that the material is cast in a regular, continuous flow without interruptions, to avoid defects in flatness. Adapt the width of the spread to the capacity of the mixer pump and layer thickness, normally as a rule of thumb no more than 8 - 10 meters without dividers. If there are high demands for flatness of the surface, the width should be as narrow as possible.
The levelling layer of **Uniplan 350 DR** will be ready to receive resilients, carpet, ceramic and multi-layer wood floor coverings fixed with adhesives after 1 - 5 days at +23°C, 50 % RH and certain air exchange (time can vary depending on the thickness of the levelling layer, the ambient room temperature and humidity).
Layer thickness up to 30 mm after 1 day, up to 40 mm after 2 days, up to 50 mm after 3 days and up to 60 mm after 5 days. Carefully check the moisture content of the levelling layer and that the entire floor construction below the levelling compound is sufficiently dry before applying adhesive and surface covering. Follow the guidelines in the local standard.
For moisture-sensitive surface covering such as wood follow the guidelines from the manufacturer.

CLEANING

Remove **Uniplan 350 DR** from tools and equipment with water whilst still fresh. Hardened material must be removed mechanically.

CONSUMPTION

1.75 kg/m^2 per mm thickness.
6 mm = 10.5 kg/m^2.
10 mm = 17.5 kg/m^2.

PACKAGING

Uniplan 350 DR is available in 20 kg bags, 1200 kg big-bag and bulk.

STORAGE

Uniplan 350 DR remains stable for 9 months if stored in its original packaging in a cool dry place.

SAFETY INSTRUCTIONS FOR PREPARATION AND INSTALLATION

Instructions for the safe use of our products can be found on the latest version of the SDS available from our website **www.mapei.no**

PRODUCT FOR PROFESSIONAL USE.

TECHNICAL DATA (typical values)

In compliance with: – EN 13813 CT-C30-F7-A1$_{FL}$

PRODUCT IDENTITY	
Consistency:	fine powder
Colour:	grey
Bulk density:	1200 kg/m^3
Dry solids content:	100 %
Grain size (D_{max}):	1 mm
Emissions:	EC1 Plus – very low emission

APPLICATION DATA (at +23°C and 50 % RH)	
Layer thickness per coat:	from 6 - 60 mm
Recommended water amount:	3.8 - 4.0 liters per 20 kg bag (19 - 20 %) for levelling 3.2 - 3.6 liters per 20 kg bag (16 - 18 %) for slopes
Density of mix:	2150 kg/m^3
pH-value of mix:	approx.11
Application temperature range:	from +10°C to +30°C
Pot life:	approx. 20 - 30 minutes
Setting time:	35 - 60 minutes
Set to light foot traffic:	approx. 2 - 4 hours
Ready for covering:	1 - 5 days depending on thickness and drying conditions
Flow ratio at 19 % water (EN12706 – ring 30x50 mm):	125 - 140 mm
Flow ratio at 19 % water (SS923519 – ring 50x22 mm):	140 - 155 mm

FINAL PERFORMANCES			
Performance characteristics	**Test method**	**Requirements according to EN 13813 for cementitious screeds**	**Typical values**
Compressive strength:	EN 13892-2	5 < N/mm² < 80 (after 28 days)	**+23°C** 24 hours: 12 N/mm² 7 days: 22 N/mm² 28 days: 31 N/mm²
Flexural strength:	EN 13892-2	1 < N/mm² < 50 (after 28 days)	**+23°C** 24 hours: 3 N/mm² 7 days: 5 N/mm² 28 days: 7 N/mm²
Surface tensile strength (pull-off):	GBR Trade Standard		28 days: > 1.5 N/mm² (MPa)
Adhesion to concrete:	EN 13892-8		> 1.0 N/mm² (MPa)
Density of hardened material:			**+23°C** 28 days: 1950 kg/m³
Shrinkage:	EN 13454-2 EN 13872	> 10 mm	**+23°C** 28 days: < 0.3 ‰ (mm/m)
Reaction to fire:	EN 13501-1	Value declared by producer	$A1_{FL}$
pH-value of hardened material:			approx. ≤ 9

WARNING

Although the technical details and recommendations contained in this product data sheet correspond to the best of our knowledge and experience, all the above - information must, in every case, be taken as merely indicative and subject to confirmation after long-term practical application: for this reason, anyone who intends to use the product must ensure beforehand that it is suitable for the envisaged application: in every case, the user alone is fully responsible for any consequences deriving from the use of the product.

Please refer to the current version of the technical data sheet, available from our web site www.mapei.no

LEGAL NOTICE

The contents of this Technical Data Sheet ("TDS") may be copied into another project-related document, but the resulting document shall not supplement or replace requirements per the TDS in effect at the time of the MAPEI product installation. For the most up-to-date TDS and warranty information, please visit our website at www.mapei.no

ANY ALTERATIONS TO THE WORDING OR REQUIREMENTS CONTAINED IN OR DERIVED FROM THIS TDS SHALL VOID ALL RELATED MAPEI WARRANTIES.

Mapei AS

Vallsetvegen 6, 2120 Sagstua, Norge

+47 62 97 20 00 www.mapei.no post@mapei.no

10320-10-2026-gbxno

Any reproduction of texts, photos and illustrations published here is prohibited and subject to prosecution